

## Sumiliteresin® PR-53804 BI

Phenolic

SBHPP

### Описание материалов:

SUMILITERESIN® PR-53804 BI is a powder novolac phenolic resin modified CNSL.

Characteristics

SUMILITERESIN® PR-53804 BI is a powder novolac phenolic resin which contained 20% cashew modified and hexamine content about 7%, middle molecular weight.

For Friction Material : improve flexibility, high friction coefficient and good feeling of braking.

For Rubber reinforcing : easy mixture compound, improve hardness with good flexibility.

Главная Информация		
Характеристики	Высокое трение	
	Хорошая гибкость	
	Средний Молекулярный вес	
Внешний вид	Коричневый	
Формы	Порошок	
Физический	Номинальное значение	Единица измерения
Длина потока (125°C)	3.00 - 5.50	cm
Анализ сита-106µm		%
Тепловой	Номинальное значение	Единица измерения
Температура плавления	82.0 - 95.0	°C
Uncured Properties	Номинальное значение	Единица измерения
Gel Time (165°C)	0.25 - 0.58	min

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

### Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

