

Sumiliteresin® PR-F-85 I

Phenolic

SBHPP

Описание материалов:

SUMILITERESIN® PR-F-85 I is a bis-phenol-A modified novolak phenolic resin. It is generally apply for foundry.

Characteristics

SUMILITERESIN® PR-F-85 I is a flake phenolic resin with good properties in foundry manufacture. It is designed in High molecule number and High modified with bis-phenol-A in order to get low thermal expansion, anti peelback and high stick point. RCS will no be easy to be agglomeration. It is preferable add hexamine about 15%/resin when applied in resin coated sand (RCS).

Главная Информация		
Внешний вид	Коричневый	
Формы	Шелковистый	
Физический	Номинальное значение	Единица измерения
Длина потока (125°C)	2.50 - 5.50	cm
Тепловой	Номинальное значение	Единица измерения
Температура плавления	66.0 - 86.0	°C
Uncured Properties	Номинальное значение	Единица измерения
Gel Time (150°C)	0.67 - 1.2	min

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

